

## Polycat 35 catalyst CAS25441-67-9 Evonik Germany

### Overview

Polycat 35 is a tertiary amine-based foaming catalyst that facilitates urea (water-isocyanate) reactions in a variety of hard and soft polyurethane foam applications. It is the industry standard foaming catalyst for soft foams and is used in TDI-based soft foam systems such as mattresses, seats, and automobiles. It is also used in combination with trimer catalysts in PIR laminated paperboard formulations. Polycat 35 can also be used in MDI, TDI/MDI, MDI High Resilience (HR) soft molding foams as well as self-crusting and microcellular systems. It has a shelf life of 36 months.

### Physical and chemical properties

Appearance: Clear colorless liquid

Odor: Slight ammonia odor

Specific gravity: 1.040

Boiling point: 200°C

Flash point: 100°C

Water soluble: miscible

Solubility in organic solvents: miscible

## Features

- Promotes urea (water-isocyanate) reaction
- Used in a variety of hard and soft polyurethane foam applications
- Industry standard foaming catalyst for soft foams
- For TDI-based soft foam systems, such as mattresses, seats, and automobiles
- Used in combination with trimer catalysts in PIR laminated board formulations
- Also available in MDI, TDI/MDI, MDI High Resilience (HR) soft molded foams as well as self-crusting and microcellular systems
- The shelf life is 36 months

## Application

- Soft polyurethane foam
- On-site pouring polyurethane system
- PIR laminated cardboard
- TDI, TDI/MDI, MDI High Resilience (HR) Soft molded foam
- Self-crusting foam
- Microcellular foam

## Pros

**Newtop Chemical Materials (Shanghai) Co.,Ltd.**

Address: Rm1104 ,No. 258, West SongXing Road, BaoShan District, Shanghai, China.

Mobile Phone: +0086-183 0190 3151 E-mail: [info@newtopchem.com](mailto:info@newtopchem.com) [www.newtopchem.com](http://www.newtopchem.com)

- Promotes urea (water-isocyanate) reaction
- Used in a variety of hard and soft polyurethane foam applications
- Industry standard foaming catalyst for soft foams
- Can be used in combination with trimer catalysts
- Shelf life is 36 months

### **shortcoming**

- Corrosive to certain metals
- Can have a strong odor
- Combustible

### **Similarities and differences with similar products**

Polycat 35 is similar to other tertiary amine-based foaming catalysts in that it promotes the urea (water-isocyanate) reaction. However, it has a number of advantages over other products, including its use in a variety of applications, industry standard status for soft foams, and ability to be combined with trimer catalysts.



### Precautions for Use

- Wear gloves and safety goggles when handling Polycat 35.
- Avoid contact with skin and eyes.
- Keep away from heat sources and open flames.
- Store in a cool, dry place.
- Dispose of it properly according to local regulations.

### Additional information

- Polycat 35 is a registered trademark of Evonik Industries.
- For more information, visit the Evonik website.

### Shelf life:

Newtop Chemical Materials (Shanghai) Co.,Ltd.

Address: Rm1104 ,No. 258, West SongXing Road, BaoShan District, Shanghai, China.

Mobile Phone: +0086-183 0190 3151 E-mail: [info@newtopchem.com](mailto:info@newtopchem.com) [www.newtopchem.com](http://www.newtopchem.com)

Remained unopened for two years

**Storage and Transportation:**

Should be sealed, stored in a dry cool ventilated warehouse

**Packing:**

200KG/ barrel storage: It is recommended to store in a dry and cool area with proper ventilation. After the original packaging, please fasten the packaging cover as soon as possible to prevent moisture and other substances from mixing and affecting the product performance. Do not inhale dust and avoid contact between skin and mucous membrane. Smoking, eating and drinking are prohibited in the workplace. Shower and change after work. Store contaminated clothes separately and use them after washing. Practice good hygiene.

**Technical support and business contacts E-mail: [info@newtopchem.com](mailto:info@newtopchem.com)**